



STRUCTUROC E.T.

Cement-based fast setting repair mortar
for thin applications

STRUCTUROC E.T. is a rapid setting, polymer modified, shrink resistant, high early strength, cement based patching and topping system for restoration and leveling of rough horizontal concrete substrates. It is ready for return of rubber wheeled traffic in 120 minutes, and can be used for repairs down to 3 mm (1/8") in thickness and be feathered edge.

■ USES

Interior horizontal repairs and leveling of concrete surfaces.

TYPICAL USES:

- Floors prior to application of epoxy coatings
- Distressed or worn concrete floor surfaces
- Step repair
- Manufacturing, storage and shipping areas
- Distribution centers and warehouse floors
- Aisles and other industrial repair situations

■ PRODUCT FEATURES

- Fast turn around time for early return of traffic
- Can be epoxy coated after 2 hours @ 21°C (70°F)
- No primer or bonding agent required
- Excellent bond to concrete substrate
- Rapid, high early strength gain
- Shrink resistant
- Expands and contracts at a rate similar to concrete
- Ready to use with addition of water
- Easy to place
- Can be tiled, carpeted or coated within 2 hours

■ SURFACE PREPARATION

Surface must be saturated but free of standing water (saturated surface dry, SSD). Surface must be dry, sound, clean, free of oil, wax, sealers, asphalt, paint, dirt, gypsum or latex patches, urethanes, adhesives, loose material and any contaminate that may act as a bond breaker. Weak surfaces must be cleaned by mechanical means such as chipping, shot-blasting or grinding.

■ PRIMING

No primer required.

■ PRODUCT MIXING

- Mix only the amount of STRUCTUROC E.T. that can be placed within 15 minutes.
- Add 4.5 to 4.75 liters of clean mixing water to a clean recipient.
- Slowly add the STRUCTUROC E.T. material while continuously mixing with a 3/4" heavy duty drill with mixing paddle.
- Mix continuously for 3 minutes until a lump free consistency is obtained.

■ PRODUCT APPLICATION

PLACING

Once a homogenous mix is obtained, place material on the repair area and spread evenly with a wood or magnesium trowel.

FINISHING

When material tightens up, finish material surface using a steel trowel.

MATERIAL PHYSICAL PROPERTIES @ 22°C (72°F)

COMPRESSIVE STRENGTH ASTM C109 @ 7 DAYS			HARDENING	
2 hours	6.9 MPa	(1,000 psi)	Initial set	22-35 minutes
1 day	20.7 MPa	(3,500 psi)	Final set	35-45 minutes
7 days	34.5 MPa	(5,000 psi)	LENGTH CHANGE ASTM C157 @ 7 DAYS	
28 days	41.4 MPa	(6,000 psi)	Wet + 0.04%	Dry - 0.011%



STRUCTUROC E.T.

Cement-based fast setting repair mortar
for thin applications

■ CURING

Allow STRUCTUROC E.T. to air cure. Polyethylene sheets or a membrane approved by SOLHYDROC INC. may be used to protect surface (while curing) during hot, windy, or other questionable ambient conditions.

■ ESTIMATING / YIELD

STRUCTUROC E.T. is supplied in 22.7 kg (50 lb) bags. Each 22.7 kg (50 lb) bag of STRUCTUROC E.T. mixed with 4.75 liters of clean mixing water will cover approximately 4.1 m² (44 ft²) at a thickness of 3 mm (1/8").

■ PRECAUTIONS / RESTRICTIONS

- Apply to pre saturated surface only
- Do not apply on fresh concrete
- Do not add admixture to this product
- If patches will receive considerable traffic, consider square cutting instead of featheredging to be assured of longer serviceable life of edges.
- STRUCTUROC E.T. is not a precision, non shrink grout. For grouting needs refer to literature for SOLHYDFLOW GROUT or SOLHYDGROUT EPOXY HS.
- STRUCTUROC E.T. should not be placed on hot substrates over 32°C (90°F) or under 5°C (40°F).
- STRUCTUROC E.T. should not be placed in ambient temperatures under 5°C or when temperatures will be below 5°C (40°F) within 24 hours of placement.
- Avoid applications of STRUCTUROC E.T. where it is constantly immersed if it is not coated or covered by an impermeable material.

■ PACKAGING

STRUCTUROC E.T.:

22.7 kg (50 lbs) bag
56 bags per pallet

■ RECOMMENDED TOOLS

The following tools will assure a cost effective, satisfactory installation:

- Steel, Wooden or Magnesium Trowels
- 3/4" Heavy Duty drill with mixing paddles
- Mortar mixer (for large volume)

■ CLEANING

Use soap and water to clean all tools immediately after use.

■ STORAGE

STRUCTUROC E.T. must be stored in a temperate area to avoid freezing of this product. Can be kept in unopened bags for 12 months.

■ SAFETY

See Material Safety Data Sheet.

BMQ SOLUTIONS WARRANTS that the product conforms to its chemical description and is reasonably fit for the purpose stated on its Technical Data Sheet when used in accordance with its directions. BMQ Solutions makes NO OTHER WARRANTY either expressed or implied.
Buyer assumes all risk in handling.

For Professional Use Only
